

Belzona 8311

FN10112 (NATO FLUID)



INSTRUCTIONS FOR USE

Belzona® 8311 is supplied in 0.5 litre containers with a spraying pump. The top of the container is first removed and the seal punctured. The spraying pump is screwed on and the **Belzona® 8311** can then be sprayed by simply pumping the trigger. The jet can be adjusted by screwing the nozzle regulator.

PENETRATING

Spray or brush on to the seized part and allow sufficient time for the **Belzona® 8311** to penetrate. Severe cases may require two applications.

For maximum penetration, dilute the **Belzona® 8311** with up to an equal volume of white spirit.

LUBRICATING

Spray on to the area requiring lubrication. Alternatively, dip the components in the **Belzona® 8311** in a dipping bath.

DE-WATERING

Spray on to the affected area, ensuring that the water released is able to drain away.

PROTECTING AGAINST CORROSION

After cleaning the surface, spray or brush the **Belzona® 8311** on to the surface taking care that the material penetrates any irregularities in the surface.

On Production lines, the parts to be treated can be dipped into a bath of the **Belzona® 8311**.

SURFACE PREPARATION

Wash any part to be treated with fresh water to remove silt or heavy dirt.

REMOVAL OF BELZONA® 8311

If necessary, e.g. where a clean surface is required prior to painting, the film of **Belzona® 8311** is easily removed with white spirit or alkaline cleaners.

CONTACT WITH OXYGEN

Do not apply **Belzona® 8311** to components in contact with pure oxygen.

ELECTRIC MOTORS

After application of **Belzona® 8311**, electrical motors should be run light for a few minutes until a megger test indicates that the motor can be put back into service.

FRICITION DRIVE ASSEMBLIES

Contact of **Belzona® 8311** with these assemblies should be avoided as it will result in slippage. In cases of accidental contact, remove with white spirit and clean rags.

TECHNICAL DATA

CLOSED CUP FLASH POINT

100°F (38°C)

COMPATIBILITY WITH OILS

Complete compatibility with mineral, vegetable and glycol or ester types.

EFFECTS ON PLASTICS

No effect on phenolics, polyethylene, polyesters, nylon and rigid PVC. Plasticizers are extracted from flexible PVC.

EFFECTS ON RUBBERS

No effect on neoprene and other oil resistant rubbers but natural rubber and S.B.R. will swell with prolonged contact. Uncured rubbers, e.g. pressure sensitive adhesives on wrapping tapes, will be dissolved.

EFFECTS ON PAINTED SURFACES

No effect on polyurethane, epoxy and old alkyd paint. New alkyd paint may be softened and blistered.

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2023 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

